

CARACTERÍSTICAS DE PRODUCTO

Espesor	8/1 mm	8.6/0.6 mm	9.5/0.6 mm	12/2 mm	14/4 mm
Ancho	127 mm	127 mm	127 mm	120/122/125 mm	150/190 mm
Largo	400 - 1200 mm (10% en 400 mm)	400 - 1200 mm (50% en 1200 mm)	910 mm (10% en 455 mm)	400 - 1200 mm (20% en 400 mm)	1995 mm
Centro	Eucalipto	HDF	Eucalipto	Eucalipto	Pino
Densidad	700 kg/m ³	850-870 kg/m ³	700 kg/m ³	700 kg/m ³	500 kg/m ³
Espesor de chapa	1 mm	0.6 mm	0.6 mm	2 mm	4 mm
Espesor del centro	7 mm	8 mm	8.9 mm	10 mm	2 + 8 mm
N° de capa del centro	5	3	5	5	3
Tipo de barniz	UV	UV	UV	UV	UV
Tipo de adhesivo	E2	CARB2	E1	E1	E1
Brillo	30% - 40%	10% - 15%	30% - 40%	30% - 40%	+/- 35%
N° de piezas/caja	20	16	16	12	10
Tratamiento	Prensa Fría	Prensa Caliente	Prensa Caliente	Prensa Caliente	Prensa Caliente
Perfil	T&G	Click	T&G	T&G	T&G
Tolerancias	+/- 0.2 mm	+/- 0.3 mm	+/- 0.2 mm	+/- 0.2 mm	+/- 0.2 mm

ESPECIES DISPONIBLES



Acacia



Birch



Cumarú
Shihuahuaco



Ipe



Nogal



Roble



Jatoba



Sapelli

Nota: Otras especies disponibles a solicitud.